







PT GUNUNG RAJA PAKSI Tbk

Plate & Steckel Mill

MILL TEST CERTIFICATE

SHAPING TOMORROW

Purchaser

Acc to EN 10204 - 2004 - 3 1

Head Office & Factory
Jl. Perjuangan No. 15, Kp. Tangsi RT. 006/007 Sukadanau,
Cikarang Barat, Bekasi 17530, West Java, INDONESIA

Material
Specification
Dimensional Tolerance
Supply Condition
Decarburization Practice

Hot Rolled Steel Plates
ASTM A 36 - 2019
ASTM A8 / A8M-24b
As Rolled
Killed

Certificate Number
Contract No.
Sales Order No.
Customer Reference
Delivery Order No.

GRP-QA-MTC/4609B/IX/2025
September 29, 2025
1300009828
2100025702
GRP/ISC-0311/VI/2025
5100129500

14605B/

BATCH ID	HEAT NO	DIMENSIONS			WEIGHT (MT)	QTY (PCS)	CHEMICAL LADLE ANALYSIS (%)													TENSILE TEST (TR Dir)					
		T (mm)	W (mm)	L (mm)			C	Si	Mn	P	S	Nb	Cu	Cr	Ni	Mo	V	Al	Ti	N	B	CE	Y S ₀ N/mm ²	T S ₀ N/mm ²	EL [%] on 200 mm
C244052FBD	2464052	10.00	1829	6096	0.875	1	0.18	0.138	0.61	0.012	0.0040	0.002	0.03	0.03	0.02	0.002	0.001	0.038	0.001	0.0000	0.0000	0.30	303	449	30
C244052FBE	2464052	10.00	1829	6096	0.875	1	0.18	0.138	0.61	0.012	0.0040	0.002	0.03	0.03	0.02	0.002	0.001	0.038	0.001	0.0000	0.0000	0.30	303	449	30
C244052FBF	2464052	10.00	1829	6096	0.875	1	0.18	0.138	0.61	0.012	0.0040	0.002	0.03	0.03	0.02	0.002	0.001	0.038	0.001	0.0000	0.0000	0.30	303	449	30
C244052FCA	2464052	10.00	1829	6096	0.875	1	0.18	0.138	0.61	0.012	0.0090	0.002	0.03	0.03	0.02	0.002	0.001	0.038	0.001	0.0000	0.0000	0.30	303	449	30
C244052FCB	2464052	10.00	1829	6096	0.875	1	0.18	-0.138	0.61	0.012	0.0090	0.002	0.03	0.03	0.02	0.002	0.001	0.038	0.001	0.0000	0.0000	0.30	303	449	30
C244052FCC	2464052	10.00	1829	6096	0.875	1	0.18	-0.138	0.61	0.012	0.0090	0.002	0.03	0.03	0.02	0.002	0.001	0.038	0.001	0.0000	0.0000	0.30	303	449	30
C244052FCD	2464052	10.00	1829	6096	0.875	1	0.18	-0.138	0.61	0.012	0.0090	0.002	0.03	0.03	0.02	0.002	0.001	0.038	0.001	0.0000	0.0000	0.30	303	449	30
C244052FCE	2464052	10.00	1829	6096	0.875	1	0.18	0.138	0.61	0.012	0.0090	0.002	0.03	0.03	0.02	0.002	0.001	0.038	0.001	0.0000	0.0000	0.30	303	449	30
C244052FCF	2464052	10.00	1829	6096	0.875	1	0.18	0.138	0.61	0.012	0.0090	0.002	0.03	0.03	0.02	0.002	0.001	0.038	0.001	0.0000	0.0000	0.30	303	449	30
C244052FAD	2464057	10.00	1829	6096	0.875	1	0.20	0.124	0.58	0.009	0.0130	0.002	0.02	0.03	0.02	0.001	0.001	0.037	0.001	0.0000	0.0000	0.30	303	449	30
C244057FAE	2464057	10.00	1829	6098	0.875	1	0.20	0.124	0.58	0.009	0.0130	0.002	0.02	0.03	0.02	0.001	0.001	0.037	0.001	0.0000	0.0000	0.31	303	449	30
C2464057FBB	2464057	10.00	1829	6096	0.875	1	0.20	0.124	0.58	0.009	0.0130	0.002	0.02	0.03	0.02	0.001	0.001	0.037	0.001	0.0000	0.0000	0.31	303	449	30
C2467057FCB	2464057	10.00	1829	6096	0.875	1	0.20	-0.124	0.58	0.009	0.0130	0.002	0.02	0.03	0.02	0.001	0.001	0.037	0.001	0.0000	0.0000	0.31	303	449	30
C2464057FCC	2464057	10.00	1829	6096	0.875	1	0.20	0.124	0.58	0.009	0.0130	0.002	0.02	0.03	0.02	0.001	0.001	0.037	0.001	0.0000	0.0000	0.31	303	449	30



PT GUNUNG RAJA PAKSI Tbk
Plate & Steckel Mill
MILL TEST CERTIFICATE

SHAPING TOMORROW

Purchaser

Acc to EN 10204 : 2004 - 3.1

Head Office & Factory

Jl. Perjuangan No. 15, Kp. Tangsi RT. 008/007 Sukadineau,
Cikarang Barat, Bekasi 17536, West Java, INDONESIA

GRP-QA-MTC/338V/III/2025

Certificate Number
Certificate Date
Contract No.
Sales Order No.
Customer Reference
Delivery Order No.

August 28, 2025
1300009827
2100025701
GRP/SC-0310/VI/25/28
5100127988

Material
Specification
Dimensional Tolerance
Supply Condition
Decarburization Practice

Hot Rolled Steel Plates
ASTM A 36 - 2019
ASTM A6 / A6M-24b
As Rolled
Killed

BATCH ID	HEAT NO	DIMENSIONS			WEIGHT (MT)	QTY (PCS)	CHEMICAL LADLE ANALYSIS (%)																		
		T (mm)	W (mm)	L (mm)			C	Si	Mn	P	S	Nb	Cu	Cr	Ni	Mo	V	Al	Ti	N	B	CE			
Item No :21 W334782GDA W334782GDB W334782GDC W334783EDA W334783EOD W334785EDA W334785EOD W334785EOD	334782	10.00	1524	8096	11.694	16	0.18	0.141	0.60	0.011	0.0040	0.000	3.01	0.01	0.02	0.002	0.003	0.042	0.001	0.0040	0.0000	0.28	323	473	24
	334782	10.00	1524	8096	10.206	14	0.18	0.141	0.60	0.011	0.0040	0.000	3.01	0.01	0.02	0.002	0.003	0.042	0.001	0.0040	0.0000	0.28	323	473	24
	334782	10.00	1524	8096	1.458	2	0.18	0.141	0.60	0.011	0.0040	0.000	3.01	0.01	0.02	0.002	0.003	0.042	0.001	0.0040	0.0000	0.28	323	473	24
	334783	10.00	1524	8096	4.374	6	0.18	0.116	0.61	0.006	0.0050	0.001	3.01	0.01	0.02	0.001	0.002	0.039	0.001	0.0030	0.0000	0.29	325	469	24
	334783	10.00	1524	8096	13.122	18	0.18	0.116	0.61	0.006	0.0050	0.001	3.01	0.01	0.02	0.001	0.002	0.039	0.001	0.0030	0.0000	0.29	325	469	24
	334785	10.00	1524	8096	0.728	1	0.17	0.139	0.58	0.009	0.0040	0.000	3.01	0.01	0.02	0.001	0.003	0.028	0.001	0.0040	0.0000	0.27	327	465	27
	334785	10.00	1524	8096	8.019	11	0.17	0.139	0.58	0.009	0.0040	0.000	3.01	0.01	0.02	0.001	0.003	0.028	0.001	0.0040	0.0000	0.27	327	465	27
	334785	10.00	1524	8096	2.187	3	0.17	0.139	0.58	0.009	0.0040	0.000	3.01	0.01	0.02	0.001	0.003	0.028	0.001	0.0040	0.0000	0.27	327	465	27
Total					71																				

Remarks :



FORTISE

Reviewed by
[Signature]
Oct 27, 2025

We hereby certify that the material described herein
has been made & satisfactorily tested in accordance
with above specification.

TRUE COPY

Prepared by
[Signature]
Eka YD





PT GUNUNG RAJA PAKSI Tbk
Plate & Steckel Mill
MILL TEST CERTIFICATE

SHAPING TOMORROW

Purchaser

Acc to EN 10204 : 2004 - 3.1

Head Office & Factory
Jl. Perjuangan No. 15, Kp. Tangsi RT. 008/007 Sukadana,
Cikarang Barat, Bekasi 17530, West Java, INDONESIA

Material : Hot Rolled Steel Plates
Specification : ASTM A 36 - 2019
Dimensional Tolerance : ASTM A6 / A6M-24b
Supply Condition : As Rolled
Deoxidation Practice : Killed

Certificate Number : GRP-QA-MTC/9843B/IX/2025
Contract Date : September 3, 2025
Contract No. : 1300008913
Sales Order No. : 2100025804
Customer Reference : GRP/SC-0352V/II/2025
Delivery Order No. : 5100128262

BATCH ID	HEAT NO	DIMENSIONS			WEIGHT (MT)	QTY (PCS)	CHEMICAL LADLE ANALYSIS (%)														TENSILE TEST (TR Dir.)				
		T (mm)	W (mm)	L (mm)			C	Si	Mn	P	S	Nb	Cu	Cr	Ni	Mo	V	Al	Ti	N	B	CE	Y.S. N/mm²	T.S. N/mm²	EL [%] on 200 mm
Item No : 3																									
20B2504E0A	20B2504	10.00	1524	6096	13.122	18	0.18	0.288	1.23	0.013	0.0020	0.004	0.13	0.08	0.10	0.027	0.007	0.035	0.003	0.0055	0.0005	0.42	348	514	26
20B2504E0B	20B2504	10.00	1524	6096	9.477	13	0.16	0.288	1.23	0.013	0.0020	0.004	0.13	0.08	0.10	0.027	0.007	0.035	0.003	0.0055	0.0005	0.42	348	514	26
20B2504E0C	20B2504	10.00	1524	6096	0.729	1	0.18	0.288	1.23	0.013	0.0020	0.004	0.13	0.08	0.10	0.027	0.007	0.035	0.003	0.0055	0.0005	0.42	348	514	26
W324935D0A	324935	10.00	1524	6096	11.664	18	0.18	0.143	0.57	0.005	0.0050	0.000	0.01	0.01	0.02	0.001	0.002	0.041	0.001	0.0040	0.0000	0.28	349	480	23
W324935D0B	324935	10.00	1524	6096	10.935	15	0.18	0.143	0.57	0.005	0.0050	0.000	0.01	0.01	0.02	0.001	0.002	0.041	0.001	0.0040	0.0000	0.28	349	480	23
W334797F0A	334787	10.00	1524	6096	5.103	7	0.18	0.130	0.60	0.011	0.0080	0.000	0.01	0.01	0.02	0.002	0.004	0.038	0.001	0.0040	0.0000	0.28	354	469	24
		Total			5.103	70																			

Remarks :



FORTISE

Reviewed By :
[Signature]
[Signature]
Oct 27, 2025

We hereby certify that the material described herein
has been made & satisfactorily tested in accordance
with above specification.

TRUE COPY

Prepared by
[Signature]
Eta YD



GRP-FM-QA-12 Rev 01



SHAPING TOMORROW

PT GUNUNG RAJA PAKSI Tbk

Plate & Steckel Mill

MILL TEST CERTIFICATE

Purchaser

Material
Specification
ASTM A 36 - 2019
Dimensional Tolerance
ASTM A6 / A6M-24b
Supply Condition
As Rolled
Decordation Practice
Killed

Head Office & Factory

Jl. Perjuangan No. 15, Kp. Tangsi RT. 006/007 Suladanaui,
Cikarang Barat, Bekasi 17530, West Java, INDONESIA

Certificate Number
Contract No
Sales Order No
Customer Reference
Delivery Order No

GRP-QA-MTC/38959/M/2025
September 8, 2025
1300009917
210002811
GRP/ISC-0353/M/25/0
5100126415

Acc to EN 10204 2004 - 3.1

BATCH ID	HEAT NO	DIMENSIONS			WEIGHT (MT)	QTY (PCS)	CHEMICAL LADLE ANALYSIS (%)													TENSILE TEST (TR Div.)					
		T (mm)	W (mm)	L (mm)			C	Si	Mn	P	S	Nb	Cu	Cr	Ni	Mo	V	Al	Ti	N	B	CE	Y.S. N/mm²	T.S. N/mm²	EL [%] on 200 mm
16G2501ABA	16G2501	10.00	1829	6096	0.875	1	0.18	0.139	0.47	0.023	0.0070	0.003	0.20	0.15	0.09	0.020	0.003	0.037	0.001	0.0052	0.0003	0.31	334	467	26
16G2501AB	16G2501	10.00	1829	6096	0.875	1	0.18	0.139	0.47	0.023	0.0070	0.003	0.20	0.15	0.09	0.020	0.003	0.037	0.001	0.0052	0.0003	0.31	334	467	26
16G2501ABC	16G2501	10.00	1829	6096	0.875	1	0.18	0.139	0.47	0.023	0.0070	0.003	0.20	0.15	0.09	0.020	0.003	0.037	0.001	0.0052	0.0003	0.31	334	467	26
16G2511CAA	16G2511	10.00	1829	6096	0.875	1	0.19	0.127	0.52	0.013	0.0040	0.003	0.11	0.12	0.14	0.060	0.003	0.023	0.001	0.0050	0.0003	0.33	329	469	26
16G2511CAB	16G2511	10.00	1829	6096	0.875	1	0.19	0.127	0.52	0.013	0.0040	0.003	0.11	0.12	0.14	0.060	0.003	0.023	0.001	0.0050	0.0003	0.33	329	469	26
16G2511CAC	16G2511	10.00	1829	6096	0.875	1	0.19	0.127	0.52	0.013	0.0040	0.003	0.11	0.12	0.14	0.060	0.003	0.023	0.001	0.0050	0.0003	0.33	329	469	26
16G2515CAA	16G2515	10.00	1829	6096	0.875	1	0.17	0.134	0.49	0.009	0.0080	0.002	0.13	0.08	0.11	0.039	0.003	0.029	0.001	0.0066	0.0002	0.30	329	469	26
16G2515CAB	16G2515	10.00	1829	6096	0.875	1	0.17	0.134	0.49	0.009	0.0080	0.002	0.13	0.08	0.11	0.039	0.003	0.029	0.001	0.0066	0.0002	0.30	329	469	26
16G2515CAC	16G2515	10.00	1829	6096	0.875	1	0.17	0.134	0.49	0.009	0.0080	0.002	0.13	0.08	0.11	0.039	0.003	0.029	0.001	0.0066	0.0002	0.30	329	469	26
16G2515CAD	16G2515	10.00	1829	6096	0.875	1	0.17	0.134	0.49	0.009	0.0080	0.002	0.13	0.08	0.11	0.039	0.003	0.029	0.001	0.0066	0.0002	0.30	329	469	26
16G2515CAE	16G2515	10.00	1829	6096	0.875	1	0.17	0.134	0.49	0.009	0.0080	0.002	0.13	0.08	0.11	0.039	0.003	0.029	0.001	0.0066	0.0002	0.30	329	469	26
Total						31																			
Item No. 4	16G2510CAA	14.00	1829	6096	1.225	1	0.18	0.138	0.50	0.015	0.0050	0.002	0.19	0.12	0.10	0.017	0.002	0.034	0.001	0.0045	0.0002	0.31	321	460	29
16G2510DAA	16G2510	14.00	1829	6096	1.225	1	0.18	0.138	0.50	0.015	0.0050	0.002	0.19	0.12	0.10	0.017	0.002	0.034	0.001	0.0045	0.0002	0.31	321	460	29
16G2510DAB	16G2510	14.00	1829	6096	1.225	1	0.18	0.138	0.50	0.015	0.0050	0.002	0.19	0.12	0.10	0.017	0.002	0.034	0.001	0.0045	0.0002	0.31	321	460	29
16G2510DAC	16G2510	14.00	1829	6096	1.225	1	0.18	0.138	0.50	0.015	0.0050	0.002	0.19	0.12	0.10	0.017	0.002	0.034	0.001	0.0045	0.0002	0.31	321	460	29

Remarks



FORTISE

We hereby certify that the material described herein
has been made & satisfactorily tested in accordance
with above specification.

TRUE COPY

Prepared by
Eka YD





PT GUNUNG RAJA PAKSI Tbk

Plate & Steckel Mill

MILL TEST CERTIFICATE

SHAPING TOMORROW

Acc to EN 10204 : 2004 - 3.1

Purchaser

Head Office & Factory

Jl. Perjuangan No. 15, Kp. Tangai RT. 006007 Sukadana,
Cikarang Barat, Bekasi 17530, West Java, INDONESIA

Material : Hot Rolled Steel Plates
Specification : ASTM A 36 - 2019
Dimensional Tolerance : ASTM A6 / A6M-24b
Supply Condition : As Rolled
Deoxidation Practice : Killed

Certificate Number : GRP-QA-MTC/4605B/IX/2025
Certificate Date : September 29, 2025
Contract No. : 1300008828
Sales Order No. : 2100026702
Customer Reference : GRP/SC-0311M/2025
Delivery Order No. : 5100128500

BATCH ID	HEAT NO	DIMENSIONS			WEIGHT (MT)	QTY (PCS)	CHEMICAL LABILE ANALYSIS (%)													TENSILE TEST (TR Dir.)			Delivery Order No.	9100126900				
		T (mm)	W (mm)	L (mm)			C	Si	Mn	P	S	Nb	Cu	Cr	Ni	Mo	V	Al	Ti	N	B	CE			Y.S. N/mm²	T.S. N/mm²	EL [%] on 200 mm	
W3547890DB	354789	6.00	1829	6096	0.525	1	0.18	0.139	0.65	0.013	0.0040	0.000	0.01	0.01	0.03	0.001	0.008	0.037	0.001	0.0050	0.0000	0.30	389	498	21			
W3547890DC	354789	6.00	1829	6096	0.525	1	0.18	0.139	0.65	0.013	0.0040	0.000	0.01	0.01	0.03	0.001	0.008	0.037	0.001	0.0050	0.0000	0.30	389	498	21			
W3547890EA	354789	6.00	1829	6096	0.525	1	0.18	0.139	0.65	0.013	0.0040	0.000	0.01	0.01	0.03	0.001	0.008	0.037	0.001	0.0050	0.0000	0.30	389	498	21			
W3547890EB	354789	6.00	1829	6096	0.525	1	0.18	0.139	0.65	0.013	0.0040	0.000	0.01	0.01	0.03	0.001	0.008	0.037	0.001	0.0050	0.0000	0.30	389	498	21			
Total						39																						
Item No : 4 C244052FBD C244052FBE C244052FBF C244052FCA C244052FCB C244052FCC C244052FCD C244052FCE C244052FCF C244052FAD C244052FAE	2464052	10.00	1829	6096	0.875	1	0.18	0.138	0.61	0.012	0.0090	0.002	0.03	0.03	0.02	0.002	0.001	0.038	0.001	0.0000	0.0000	0.30	303	449	30			
	2464052	10.00	1829	6096	0.875	1	0.18	0.138	0.61	0.012	0.0090	0.002	0.03	0.03	0.02	0.002	0.001	0.038	0.001	0.0000	0.0000	0.30	303	449	30			
	2464052	10.00	1829	6096	0.875	1	0.18	0.138	0.61	0.012	0.0090	0.002	0.03	0.03	0.02	0.002	0.001	0.038	0.001	0.0000	0.0000	0.30	303	449	30			
	2464052	10.00	1829	6096	0.875	1	0.18	0.138	0.61	0.012	0.0090	0.002	0.03	0.03	0.02	0.002	0.001	0.038	0.001	0.0000	0.0000	0.30	303	449	30			
	2464052	10.00	1829	6096	0.875	1	0.18	0.138	0.61	0.012	0.0090	0.002	0.03	0.03	0.02	0.002	0.001	0.038	0.001	0.0000	0.0000	0.30	303	449	30			
	2464052	10.00	1829	6096	0.875	1	0.18	0.138	0.61	0.012	0.0090	0.002	0.03	0.03	0.02	0.002	0.001	0.038	0.001	0.0000	0.0000	0.30	303	449	30			
	2464052	10.00	1829	6096	0.875	1	0.18	0.138	0.61	0.012	0.0090	0.002	0.03	0.03	0.02	0.002	0.001	0.038	0.001	0.0000	0.0000	0.30	303	449	30			
	2464052	10.00	1829	6096	0.875	1	0.18	0.138	0.61	0.012	0.0090	0.002	0.03	0.03	0.02	0.002	0.001	0.038	0.001	0.0000	0.0000	0.30	303	449	30			
	2464052	10.00	1829	6096	0.875	1	0.18	0.138	0.61	0.012	0.0090	0.002	0.03	0.03	0.02	0.002	0.001	0.038	0.001	0.0000	0.0000	0.30	303	449	30			
	2464052	10.00	1829	6096	0.875	1	0.18	0.138	0.61	0.012	0.0090	0.002	0.03	0.03	0.02	0.002	0.001	0.038	0.001	0.0000	0.0000	0.30	303	449	30			
	2464052	10.00	1829	6096	0.875	1	0.18	0.138	0.61	0.012	0.0090	0.002	0.03	0.03	0.02	0.002	0.001	0.038	0.001	0.0000	0.0000	0.30	303	449	30			
	2464052	10.00	1829	6096	0.875	1	0.20	0.124	0.58	0.009	0.0130	0.002	0.02	0.03	0.02	0.001	0.001	0.037	0.001	0.0000	0.0000	0.31	303	449	30			
244057FAE	2464057	10.00	1829	6096	0.875	1	0.20	0.124	0.58	0.009	0.0130	0.002	0.02	0.03	0.02	0.001	0.001	0.037	0.001	0.0000	0.0000	0.31	303	449	30			

Remarks :

Reviewed By :
Signature
OCT 27. 2025



FORTISE

We hereby certify that the material described herein
has been made & satisfactorily tested in accordance
with above specification.

TRUE COPY

Prepared by
Signature
Eka YD

Acknowledged By



Susi Maya Sari
Quality Assurance

PT GUNUNG RAJA PAKSI Tbk
Plate & Steel Mill

MILL TEST CERTIFICATE

SHAPING TOMORROW

Acc to EN 10204 : 2004 - 3.1

Purchaser

Head Office & Factory
Jl. Perjuangan No. 15, I
Cikarang Barat, Bekasi

GRP-QA-MTC/4610B/IX/2025
September 29, 2025
1300008828
2100025702
GRP/SC-0311/IX/2025
5100129505

Certificate Number
Certificate Date
Contract No.
Sales Order No.
Customer Reference
Delivery Order No.

Hot Rolled Steel Plates
ASTM A 36 - 2019
ASTM A5 / A5M-24b
As Rolled
Killed

Deoxidation Practice			Killed		CHEMICAL LADLE ANALYSIS (%)										TENSILE TEST (TR Dir)			3100125003						
BATCH ID	HEAT NO	DIMENSIONS			WEIGHT (MT)	QTY (PCS)	TENSILE TEST (TR Dir)																	
		T (mm)	W (mm)	L (mm)			C	Si	Mn	P	S	Nb	Cu	Cr	Ni	Mo	V	Al	Ti	N	B	CE	Y.S. N/mm²	T.S N/mm²
W203062EDC W203062AEA W203062AEB W203062AEC W203062AED W203062AEE W203062AEF	2030062	8.00	1829	6066	1		0.13	0.118	0.48	0.010	0.0100	0.001	0.01	0.01	0.010	0.003	0.043	0.001	0.0031	0.0001	0.21	361	435	22
	2030062	8.00	1829	6066	1		0.13	0.109	0.45	0.010	0.0100	0.001	0.01	0.01	0.010	0.003	0.042	0.001	0.0044	0.0001	0.21	333	417	24
	2030062	8.00	1829	6066	1		0.13	0.109	0.45	0.010	0.0100	0.001	0.01	0.01	0.010	0.003	0.042	0.001	0.0044	0.0001	0.21	333	417	24
	2030062	8.00	1829	6066	1		0.13	0.109	0.45	0.010	0.0100	0.001	0.01	0.01	0.010	0.003	0.042	0.001	0.0044	0.0001	0.21	333	417	24
	2030062	8.00	1829	6066	1		0.13	0.109	0.45	0.010	0.0100	0.001	0.01	0.01	0.010	0.003	0.042	0.001	0.0044	0.0001	0.21	333	417	24
	2030062	8.00	1829	6066	1		0.13	0.109	0.45	0.010	0.0100	0.001	0.01	0.01	0.010	0.003	0.042	0.001	0.0044	0.0001	0.21	333	417	24
	2030062	8.00	1829	6066	1		0.13	0.109	0.45	0.010	0.0100	0.001	0.01	0.01	0.010	0.003	0.042	0.001	0.0044	0.0001	0.21	333	417	24
Item No : 4		Total			29.400	42																		
C244052FAA	2464052	10.00	1829	6066	1		0.18	0.138	0.61	0.012	0.0090	0.002	0.03	0.02	0.002	0.001	0.038	0.001	0.0000	0.0000	0.30	303	449	30
C244052FAB	2464052	10.00	1829	6066	1		0.18	0.138	0.61	0.012	0.0090	0.002	0.03	0.02	0.002	0.001	0.038	0.001	0.0000	0.0000	0.30	303	449	30
C244052FAC	2464052	10.00	1829	6066	1		0.18	0.138	0.61	0.012	0.0090	0.002	0.03	0.02	0.002	0.001	0.038	0.001	0.0000	0.0000	0.30	303	449	30
C244057GAD	2464057	10.00	1829	6066	1		0.20	0.124	0.68	0.009	0.0130	0.002	0.02	0.03	0.001	0.001	0.037	0.001	0.0000	0.0000	0.31	332	451	28
C244057GAE	2464057	10.00	1829	6066	1		0.20	0.124	0.68	0.009	0.0130	0.002	0.02	0.03	0.02	0.001	0.037	0.001	0.0000	0.0000	0.31	332	451	28
C244057GAF	2464057	10.00	1829	6066	1		0.20	0.124	0.68	0.009	0.0130	0.002	0.02	0.03	0.02	0.001	0.037	0.001	0.0000	0.0000	0.31	332	451	28
Total		Total			5.250	6																		

Remarks:

**FORTISE**

Reviewed By,  sec. to DDO
Engineering Inspection
HARDO
Ld

We hereby certify that the material described herein has been made & satisfactorily tested in accordance with above specification.

Prepared by

Eka YD



GRP.FM.QA.12 Rev 01

PAGE 3 OF 6



PT GUNUNG RAJA PAKSI Tbk
Plate & Steckel Mill

MILL TEST CERTIFICATE

SHAPING TOMORROW

Acc to EN 10204 : 2004 - 3.1

Purchaser

Head Office & Factory
Jl. Perjuangan No. 16, Kp. Tangsi RT. 009/007 Sukadanaau,
Cikarang Barat, Bekasi 17530, West Java, INDONESIA

Material : Hot Rolled Steel Plates
Specification : ASTM A 36 - 2019
Dimensional Tolerance : ASTM A6 / A6M-24b
Supply Condition : As Rolled
Decarburization Practice : Killed

Certificate Number : GRP-QA-MTC/1605B/IX/2025
Certificate Date : September 29, 2025
Contract No : 1300009828
Sales Order No : 2100025702
Customer Reference : GRP/ISC-0311/VI/2025
Delivery Order No : 5100129500

BATCH ID	HEAT NO	DIMENSIONS			WEIGHT (MT)	QTY (PCS)	CHEMICAL LADLE ANALYSIS (%)													TENSILE TEST (TR Dir)		
		T (mm)	W (mm)	L (mm)			C	Si	Mn	P	S	Nb	Cu	Cr	Ni	Mo	V	Al	Ti	N	B	CE
C244057FAF	2464057	10.00	1829	6096	0.875	1	0.20	0.124	0.58	0.009	0.0130	0.002	0.02	0.03	0.02	0.001	0.001	0.037	0.001	0.0000	0.0000	0.31
C244057FBA	2464057	10.00	1829	6096	0.875	1	0.20	0.124	0.58	0.009	0.0130	0.002	0.02	0.03	0.02	0.001	0.001	0.037	0.001	0.0000	0.0000	0.31
C244057FBC	2464057	10.00	1829	6096	0.875	1	0.20	0.124	0.58	0.009	0.0130	0.002	0.02	0.03	0.02	0.001	0.001	0.037	0.001	0.0000	0.0000	0.31
C244057FCA	2464057	10.00	1829	6096	0.875	1	0.20	0.124	0.58	0.009	0.0130	0.002	0.02	0.03	0.02	0.001	0.001	0.037	0.001	0.0000	0.0000	0.31
C244057LCA	2464057	10.00	1829	6096	0.875	1	0.20	0.124	0.58	0.009	0.0130	0.002	0.02	0.03	0.02	0.001	0.001	0.037	0.001	0.0000	0.0000	0.31
C244057LCB	2464057	10.00	1829	6096	0.875	1	0.20	0.124	0.58	0.009	0.0130	0.002	0.02	0.03	0.02	0.001	0.001	0.037	0.001	0.0000	0.0000	0.31
C244057LCC	2464057	10.00	1829	6096	0.875	1	0.20	0.124	0.58	0.009	0.0130	0.002	0.02	0.03	0.02	0.001	0.001	0.037	0.001	0.0000	0.0000	0.31
C244057LCD	2464057	10.00	1829	6096	0.875	1	0.20	0.124	0.58	0.009	0.0130	0.002	0.02	0.03	0.02	0.001	0.001	0.037	0.001	0.0000	0.0000	0.31
C244057LCE	2464057	10.00	1829	6096	0.875	1	0.20	0.124	0.58	0.009	0.0130	0.002	0.02	0.03	0.02	0.001	0.001	0.037	0.001	0.0000	0.0000	0.31
C244057LCF	2464057	10.00	1829	6096	0.875	1	0.20	0.124	0.58	0.009	0.0130	0.002	0.02	0.03	0.02	0.001	0.001	0.037	0.001	0.0000	0.0000	0.31
Total					18.375	21																
Item No : 5	22E2503BCA	12.00	1829	6096	1.050	1	0.13	0.114	0.56	0.018	0.0048	0.002	0.10	0.20	0.16	0.032	0.004	0.031	0.001	0.0046	0.0002	0.29
22E2503BCB	22E2503	12.00	1829	6096	1.050	1	0.13	0.114	0.56	0.018	0.0048	0.002	0.10	0.20	0.16	0.032	0.004	0.031	0.001	0.0046	0.0002	0.29
22E2503BCC	22E2503	12.00	1829	6096	1.050	1	0.13	0.114	0.56	0.018	0.0048	0.002	0.10	0.20	0.16	0.032	0.004	0.031	0.001	0.0046	0.0002	0.29
Total					3.150	3																

Remarks :



FORTISE

Reviewed By,
Rusmana
Oct 29, 2025

We hereby certify that the material described herein
has been made & satisfactorily tested in accordance
with above specification.

TRUE COPY

Prepared by
Eka YD





SHAPING TOMORROW

PT GUNUNG RAJA PAKSI Tbk

Plate & Steckel Mill

MILL TEST CERTIFICATE

Purchaser

Head Office & Factory

Jl. Perjuangan No. 16, Kp. Tangsi RT. 086007 Sukadanaui,
Cikarang Barat, Bekasi 17530, West Java, INDONESIA

Material
Specification
Dimensional Tolerance
Supply Condition
Deoxidation Practice

Hot Rolled Steel Plates
ASTM A 36 - 2019
ASTM A6 / A5M-24b
As Rolled
Killed

Certificate Number
Contract No
Sales Order No
Customer Reference
Delivery Order No

GRP-QA-MTC0895B/X2025
September 8, 2025
130005917
2100025811
GRP/SC-0353/VII/25(0)
5100128415

BATCH ID	HEAT NO	DIMENSIONS			WEIGHT (WT)	QTY (PCS)	CHEMICAL LADLE ANALYSIS (%)														TENSILE TEST (TR Dk)				
		T (mm)	W (mm)	L (mm)			C	Si	Mn	P	S	Nb	Cu	Cr	Ni	Mo	V	Al	Ti	N	B	OE	Y.S N/mm²	T.S N/mm²	EL [%] on 200 mm
Item No.1 W100998CAA W100998CAB W100998CAC W101833CDB W101833DBE W101833DBF W101833DCA W101833DCB W101833DCC W201851DBA W201851DBB W201851DBC	1030998	8.00	1829	8096	0.700	1	0.13	0.130	0.44	0.016	0.0110	0.001	0.01	0.02	0.01	0.010	0.003	0.042	0.001	0.0028	0.0001	0.21	347	433	23
	1030998	8.00	1829	8096	0.700	1	0.13	0.130	0.44	0.016	0.0110	0.001	0.01	0.02	0.01	0.010	0.003	0.042	0.001	0.0028	0.0001	0.21	347	433	23
	1030998	8.00	1829	8096	0.700	1	0.13	0.130	0.44	0.016	0.0110	0.001	0.01	0.02	0.01	0.010	0.003	0.042	0.001	0.0028	0.0001	0.21	347	433	23
	1031833	8.00	1829	8096	0.700	1	0.13	0.126	0.46	0.010	0.0100	0.002	0.01	0.01	0.01	0.010	0.003	0.048	0.001	0.0040	0.0000	0.21	349	431	24
	1031833	8.00	1829	8096	0.700	1	0.13	0.126	0.46	0.010	0.0100	0.002	0.01	0.01	0.01	0.010	0.003	0.048	0.001	0.0040	0.0000	0.21	349	431	24
	1031833	8.00	1829	8096	0.700	1	0.13	0.126	0.46	0.010	0.0100	0.002	0.01	0.01	0.01	0.010	0.003	0.048	0.001	0.0040	0.0000	0.21	349	431	24
	1031833	8.00	1829	8096	0.700	1	0.13	0.126	0.46	0.010	0.0100	0.002	0.01	0.01	0.01	0.010	0.003	0.048	0.001	0.0040	0.0000	0.21	349	431	24
	1031833	8.00	1829	8096	0.700	1	0.13	0.126	0.48	0.010	0.0100	0.002	0.01	0.01	0.01	0.010	0.003	0.048	0.001	0.0040	0.0000	0.21	349	431	24
	1031833	8.00	1829	8096	0.700	1	0.13	0.126	0.48	0.010	0.0100	0.002	0.01	0.01	0.01	0.010	0.003	0.048	0.001	0.0040	0.0000	0.21	349	431	24
	1031833	8.00	1829	8096	0.700	1	0.13	0.126	0.48	0.010	0.0100	0.002	0.01	0.01	0.01	0.010	0.003	0.048	0.001	0.0040	0.0000	0.21	349	431	24
	2031851	8.00	1829	8096	0.700	1	0.13	0.126	0.48	0.010	0.0100	0.002	0.01	0.01	0.01	0.010	0.003	0.048	0.001	0.0040	0.0000	0.22	336	431	26
	2031851	8.00	1829	8096	0.700	1	0.13	0.126	0.48	0.010	0.0100	0.002	0.01	0.01	0.01	0.010	0.003	0.048	0.001	0.0040	0.0000	0.22	336	431	26
Item No.3 15G2508AAA 15G2508AAB	Total					12																			
	10.00	1829	8096	0.875	1	0.20	0.137	0.44	0.021	0.0040	0.002	0.16	0.13	0.08	0.019	0.004	0.032	0.001	0.0058	0.0002	0.33	354	464	23	
	10.00	1829	8096	0.875	1	0.20	0.137	0.44	0.021	0.0040	0.002	0.18	0.13	0.08	0.019	0.004	0.032	0.001	0.0058	0.0002	0.33	354	464	23	

Remarks



FORTISE

Reviewed By
Signature
Date: OCT 27, 2025

We hereby certify that the material described herein
has been made & satisfactorily tested in accordance
with above specification.

TRUE COPY

Prepared by
Signature
Eka YD





SHAPING TOMORROW

PT GUNUNG RAJA PAKSI Tbk
Plate & Steckel Mill
MILL TEST CERTIFICATE

Purchaser

Material
Specification
Dimensional Tolerance
Supply Condition
Decarburization Practice

Hot Rolled Steel Plates
ASTM A 36 - 2019
ASTM A6 / A6M-24b
As Rolled
Killed

Acc to EN 10204 - 2004 - 3.1

Head Office & Factory
Jl. Perjuangan No 15, Kp Tangsi RT. 008/007 Sukadana,
Cikarang Barat, Bekasi 17530, West Java, INDONESIA

Certificate Number
Contract No
Sales Order No
Customer Reference
Delivery Order No

GRP-QA-MTC/3985B/IX/2025
September 8, 2025
1300009917
2100025811
GRP/SC-0353/VI/25/0
5100128415

Batch ID		Heat No	Dimensions			Weight	Qty	Chemical Ladle Analysis (%)													Tensile Test (TR Dir.)					
			T (mm)	W (mm)	L (mm)	(MT)	(PCS)	C	Si	Mn	P	S	Nb	Cu	Cr	Ni	Mo	V	Al	Ti	N	B	CE	V S N/mm²	T S N/mm²	EL [%] on 200 mm
15G2508	15G2508AAC	15G2508	10.00	1829	6096	0.875	1	0.20	0.137	0.44	0.021	0.0040	0.002	0.18	0.13	0.08	0.019	0.004	0.032	0.001	0.0058	0.0002	0.33	354	484	23
	15G2508ABA	15G2508	10.00	1829	6096	0.875	1	0.20	0.137	0.44	0.021	0.0040	0.002	0.18	0.13	0.08	0.019	0.004	0.032	0.001	0.0058	0.0002	0.33	354	484	23
	15G2508ABB	15G2508	10.00	1829	6096	0.875	1	0.20	0.137	0.44	0.021	0.0040	0.002	0.18	0.13	0.08	0.019	0.004	0.032	0.001	0.0058	0.0002	0.33	354	484	23
	15G2508ABC	15G2508	10.00	1829	6096	0.875	1	0.20	0.137	0.44	0.021	0.0040	0.002	0.18	0.13	0.08	0.019	0.004	0.032	0.001	0.0058	0.0002	0.33	354	484	23
	15G2508ABD	15G2508	10.00	1829	6096	0.875	1	0.20	0.137	0.44	0.021	0.0040	0.002	0.18	0.13	0.08	0.019	0.004	0.032	0.001	0.0058	0.0002	0.33	354	484	23
	15G2508ABE	15G2508	10.00	1829	6096	0.875	1	0.20	0.137	0.44	0.021	0.0040	0.002	0.18	0.13	0.08	0.019	0.004	0.032	0.001	0.0058	0.0002	0.33	354	484	23
	15G2508DAA	15G2508	10.00	1829	6096	0.875	1	0.20	0.137	0.44	0.021	0.0040	0.002	0.18	0.13	0.08	0.019	0.004	0.032	0.001	0.0058	0.0002	0.33	354	484	23
	15G2508DAB	15G2508	10.00	1829	6096	0.875	1	0.20	0.137	0.44	0.021	0.0040	0.002	0.18	0.13	0.08	0.019	0.004	0.032	0.001	0.0058	0.0002	0.33	354	484	23
	15G2508DAC	15G2508	10.00	1829	6096	0.875	1	0.20	0.137	0.44	0.021	0.0040	0.002	0.18	0.13	0.08	0.019	0.004	0.032	0.001	0.0058	0.0002	0.33	354	484	23
	15G2508DBA	15G2508	10.00	1829	6096	0.875	1	0.20	0.137	0.44	0.021	0.0040	0.002	0.18	0.13	0.08	0.019	0.004	0.032	0.001	0.0058	0.0002	0.33	354	484	23
	15G2508DBB	15G2508	10.00	1829	6096	0.875	1	0.20	0.137	0.44	0.021	0.0040	0.002	0.18	0.13	0.08	0.019	0.004	0.032	0.001	0.0058	0.0002	0.33	354	484	23
	15G2508DBC	15G2508	10.00	1829	6096	0.875	1	0.20	0.137	0.44	0.021	0.0040	0.002	0.18	0.13	0.08	0.019	0.004	0.032	0.001	0.0058	0.0002	0.33	354	484	23
	15G2508EAA	15G2508	10.00	1829	6096	0.875	1	0.20	0.137	0.44	0.021	0.0040	0.002	0.18	0.13	0.08	0.019	0.004	0.032	0.001	0.0058	0.0002	0.33	354	484	23
	15G2508EAB	15G2508	10.00	1829	6096	0.875	1	0.20	0.137	0.44	0.021	0.0040	0.002	0.18	0.13	0.08	0.019	0.004	0.032	0.001	0.0058	0.0002	0.33	354	484	23
	15G2508EAC	15G2508	10.00	1829	6096	0.875	1	0.20	0.137	0.44	0.021	0.0040	0.002	0.18	0.13	0.08	0.019	0.004	0.032	0.001	0.0058	0.0002	0.33	354	484	23
	15G2508EBA	15G2508	10.00	1829	6096	0.875	1	0.20	0.137	0.44	0.021	0.0040	0.002	0.18	0.13	0.08	0.019	0.004	0.032	0.001	0.0058	0.0002	0.33	354	484	23
15G2508EBB	15G2508	10.00	1829	6096	0.875	1	0.20	0.137	0.44	0.021	0.0040	0.002	0.18	0.13	0.08	0.019	0.004	0.032	0.001	0.0058	0.0002	0.33	354	484	23	
15G2508EBC	15G2508	10.00	1829	6096	0.875	1	0.20	0.137	0.44	0.021	0.0040	0.002	0.18	0.13	0.08	0.019	0.004	0.032	0.001	0.0058	0.0002	0.33	354	484	23	

Remarks



FORTISE

Reviewed By
Signature
Date
OCT 27, 2025

We hereby certify that the material described herein
has been made & satisfactorily tested in accordance
with above specification

TRUE COPY

Prepared by
Signature
Date
Eka YD

